




TEST ALKALNIH NAVADNIH BATERIJ

AA 1,5V

																
	ACTIV ENERGY Hofer	DURACELL ULTRA	VARTA Longlife MAX P.	AEROCELL Lidl	DURACELL PLUS	DURACELL (Basic)	Paradies DM	S BUDGET Spar	VARTA Longlife	POWER STAR Tuš	ALKALISK IKEA	MULLER	ENERGIZER MAX	home ENERGY (Mercator)	PHILIPS Long life	GREENCELL Extra Heavy Duty
Čas [min]	484	445	425	420	425	410	400	356	352	330	327	296	294	288	103	105
[mAh]	1390	1280	1240	1217	1228	1190	1160	1026	1006	947	942	854	836	831	325	317
																

Drobni tisk: Testi opravljani z napravo ZB2L3. Izpraznitev preko ohmskega bremena ZY 5W7R5. Vsi testi opravljani po enakem postopku, do izpraznitve baterije na 1.2V (nekateri naprave sicer delujejo tudi na 1.1V). Tok izpraznitve cca 0.175 A.

Načeloma so dražje bolj odporne proti "razlitju" elektrolita, čemur pa ta test ni bil namenjen. November 2020